

## Abrasive breakdown

Abrasive wears down to produce an operating mix of different size pellets

Shot  Starts off round, stays round.

SG Grit  Starts off angular, becomes round.

LG Grit  Starts off angular, becomes blunted.

HG Grit  Starts off angular, stays angular.

High quality shot erodes



Poor quality shot fractures

